



Chamotte Fire Brick

آجر نسوز شاموتی کوره های صنعتی

Classification:	Fireclay Brick
Main Raw Material Component:	Chamotte

Product Analysis										
Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO	MnO	P ₂ O ₅	Na ₂ O	K ₂ O	LOI
0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
%	%	%	%	%	%	%	%	%	%	%
40± 2	51±2	2-2.7	5.51	0.30	0.32	<0.01	0.19	0.31	1.11	0.15

The above data are typical of the properties of commercial Standard brick .

The data are subject to reasonable variation and therefore should not be used for Specification

purposes. They may not be regarded as committed specifications and therefore not as guaranteed properties